



SEAL WIDENING AND ACCESS SEALING

**MINIMUM FORMATION STANDARDS**

The formation shall extend down to a suitable subgrade which shall be free of organic material. As a minimum requirement, the formation shall comprise of a 150 mm compacted layer of subbase (AP65) overlaid with a 100 millimeter compacted layer of base course (AP40). The top course shall be applied as follows:

- (a) Where the adjacent road formation is sealed, the entrance shall have a bound cohesive surface formation overlaid with a coat of chip seal, consisting of hot bitumen sprayed at a rate of 1.6 to 1.9 litres / square metre and grade 4 stone chip depending on surface conditions.
- (b) Where the adjacent road formation is metalled, the new entrance formation shall be overlaid with AP20 running course.

SCALE <b>NTS</b>		SHEET TITLE	PLAN No.
		<b>VEHICLE CROSSING RURAL COMMERCIAL / INDUSTRIAL (TYPE F)</b>	<b>3000 SHEET 7</b>
		Date Stamp	01/08/2003
		ISSUE	A
		Sheet No.	1 of 1